SEVES GLASS BLOCK SEALANT

MULTI-SURFACE 1-PART INDUSTRIAL/CONSTRUCTION GRADE SILICONE SEALANT

Seves Glass Block Sealant is a one component, low modulus, neutral cure silicone sealant and adhesive specifically formulated to work with Seves Provantage®, KWiK'N-EZ®, Pegasus and Doric Glass Block Installation Systems. When fully cured, this unique VOC compliant formula offers UV stability and tenacious adhesion to all Seves installation system components. Seves Glass Block Sealant also bonds to a wide variety of building materials including PVC, concrete, glass, aluminum, painted surfaces, wood, plywood, stucco, building paper, window wrap, fiber cement, brick, stone, steel, ceramic, porcelain, masonry, plus many other common material surfaces. This product is specifically formulated to offer all weather performance to meet today's Green Building Standards.

FEATURES & BENEFITS

Multi-Surface	Excellent Weatherability	
Excellent Adhesion	Long Life	
Non-Corrosive	VOC Compliant	
Low Odor	Non-Flammable	
50% Movement Capability	Waterproof	
Permanent Flexibility		

MEETS SPECIFICATIONS: ASTM C920 Type S, Grade NS, Class 50, TT-S-00230C, TT-S-01543A, MIL-A-46106A, AAMA 808.3, 805.2, 803.3 (Type I), 802.3 (Type II); UL Recognized Component. **AVAILABLE COLORS:** Clear

100% oxime cure, clear

Longer 17-minute tooling time provides professional joint finish and weather seal ... Mildew-resistant UV-resistant Non-carrosive Cured life expectancy 20 years Scellant de blocs

seul scellant en silicone
elabore et garanti pour être utilisé
avec les blacs de verre de Seves
Glass Black
Glass Black
Durcisseur 100% en axime.
silicone transparent
Finition professionnelle et
étarchétié ous intempéres
rosurées après une durée
d'application de 17 minutes
Résistant à masiassure
Résistant a masiassure
Résistant a masiassure

Clear / Clair

PHYSICAL PROPERTIES		TEST METHOD
Cure System	Neutral/Oxime	TEOT METHOD
Movement Capability, %	±50%	ASTM C-719
Modulus	Low	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min.	500	ASTM C-1183
1/8"orifice @ 50 psi		Modified
Temperature Range	-62°F to 400°F	
Intermittent Temperature Range	450°F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	12*	MNA Method
Tack Over Time (min)	25*	ASTM C-679
Cure Rate	1/8" per 30hrs*	MNA Method
Tensile Strength (psi)	190	ASTM D-412
Elongation %	650	ASTM D-412
Durometer Shore A	15	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.7 @ 96	
Shelf Life (months)	18	
Volatile Organic Content	40 gr./liter	

^{*}All properties derived from lab conditions (77° F at 50% relative humidity)

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

SBG-021 10/20