

# Seves Glass Block

## 2-Hour Fire Rated Wall Block



**Test Method:** ASTM E-119, UL 263-19 and CAN/ULC S101-14

**Series / Line:** High Performance

**Block Size:** 19cm x 19cm x 13cm or 7.48" x 7.48" x 5.11"

**Available Patterns:** Wave and Clarity

**Heat Transmission U-Value (BTU/hr ft<sup>2</sup> °F):** 0.28

**Thermal Resistance R-value (hr ft<sup>2</sup> °F/BTU):** 3.61

### Testing Summary:

The glass block wall assembly withstood the fire exposure of ASTM E119 for a period of 120 minutes. A second, duplicate wall assembly was subjected to a hose stream test following a fire exposure of 1/2 the duration of the initial fire exposure test of 2-hr which resulted in no projection of water through the unexposed face. The wall assembly obtained a fire resistance rating of 120 minutes.

# Available Now!

**SEVES  
GLASS  
BLOCK**

Seves Glass Block, Inc.  
1.877.738.3711  
leads@sevesglassblock.com  
sevesglassblockinc.com

**Follow us on:**



