

# 2 HOUR WALL RATED FIRE RESISTANT GLASS BLOCK



## 1919/13 F-120 Fire Resistant for up to 2 Hour Rating in Vertical Panels

USE OF A MASONRY OR CONCRETE CHASE, ANGLE IRON OR FORMED CHANNEL RESTRAINT  
REQUIRED TO CONFORM WITH ASTM STANDARD

Actual: 190mm X 190mm X129.8mm 7.48in. X 7.48in. X 5.11in.

U.S. Test Method: ASTM E-119-20 Fire Resistant Test for non-loadbearing  
UL 263-19 glass block wall assemblies  
CAN/ULC-S101-14

EU. Test Classification: CSN EN 13501-2:2017 Fire Separating Construction  
EU. Test Method: CSN EN 1364-1 Fire Resistant Test for non-loadbearing  
elements – Part 1: Walls

Weight per block: 11.25 lbs. (w/ mortar 30 lbs./sf)  
Compression Strength: CSN EN 1051-1 9.0 (MPa) - 1305.34 (PSI)  
Light Transmittance: CSN EN 410 See Chart Below  
SHGC (g-value): CSN EN 410 See Chart Below  
U-Value: CSN EN 673 U-Value: 0.277 (Btu/hr ft<sup>2</sup> °F)  
R-Value: R-Value: 3.61 (hr ft<sup>2</sup> F/Btu)

Glass Block 1919/13 F120		
TYPE	Light Transmittance $\tau_v$ (1)	Solar Heat Gain Coefficient
Clear	0.69	0.64
1S	0.6	ext. 0.57 / int. 0.63
2S	0.51	0.56